
Technical information

TI G-KT/SM October 2011

® = registered trademark of BASF SE

Basotect® G+

Product description

Basotect® G+ is a light-grey, open-cell foam made of melamine resin.

Delivery and storage

Basotect is manufactured in the form of untrimmed blocks with a thin outer skin. The standard dimensions of the blocks are 2500 x 1250 x 500 mm. Special lengths can be produced upon request.

The blocks are delivered in film packaging and should be stored in a dry place. Direct and prolonged exposure to ultraviolet radiation should be avoided.

Prior to being processed, the blocks should be unwrapped and stored for a minimum of three days, preferably five days, in a standard conditioned atmosphere. The reason for this is the sorption behavior of the melamine resin. The dimensions of the blocks change as they absorb or release moisture.




Diagram 1: Dimensional change as a function of the relative indoor humidity at an ambient temperature of 23°C [73.4°F]

Properties

Physical properties

The thermoset character and the open-cell structure of the melamine resin foam translate into an attractive property profile:

- High sound absorption
- Low thermal conductivity
- High fire resistance
- Low density
- High long-term use temperatures
- No brittleness at low temperatures

Properties	Standards	Units	Values
Density	EN ISO 845	kg/m ³	9 +/-1.5
Compressive strength Average value	EN ISO 3386-1	kPa	>7
Tensile strength Average value	EN ISO 1798	kPa	>120
Elongation at break Average value	EN ISO 1798	%	>20
Fire behavior			
- Germany	DIN 4102-1		B1
- Europe	EN 13501		Upon request
- USA	UL 94		V - 0 HF-1

Table 1: Physical properties of Basotect® G+

Diagram 2 shows the thermal conductivity of Basotect® G+ as a function of the mean temperature. With its values of ≤ 0.035 W/mK at 10°C [50°F], Basotect occupies a leading position among the commercially available insulating materials.




Diagram 2: Thermal conductivity of Basotect G+. Measurement according to DIN EN 12667 or with the Lola 3 two-plate apparatus manufactured by ZAE Bayern of Würzburg, Germany

The test results from the acoustic experiments in an impedance tube according to ISO 10534-2 and in a reverberation room according to DIN EN ISO 354 are shown in Diagrams 3 and 4. In the medium and high frequency ranges, Basotect® G+ exhibits an outstanding sound absorption behavior. At low frequencies, technical acoustic improvements can be achieved, for example, by means of additional heavy layers.




Diagram 3: Degree of sound absorption of Basotect® G+ as a function of the thickness, according to ISO 10534-2 (impedance tube).




Diagram 4: Degree of sound absorption of Basotect G+ as a function of the thickness, according to DIN EN ISO 354 (reverberation room)

Chemical resistance

According to DIN EN ISO 175, Basotect® G+, as a thermoset material, is resistant to many media (Table 2). The compressive strength according to ISO 3386-1 (40% compression, 4th load cycle) and the change in sample geometry serve as evaluation criteria. The figures apply to a test temperature of 23°C [73.4°F].

Medium	Evaluation
Acids	
Formic acid 90 %	-
Acetic acid 90 %	+
Lactic acid 10 %	+
Phosphoric acid 50 %	+
Nitric acid 10 %	-
Hydrochloric acid 10 %	-
Sulfuric acid 10 %	-
Citric acid 10 %	+
Other chemicals	
Sodium hypochlorite	+
Sodium chloride solution 3.6%	+
Water	+
Hydrogen peroxide 30 %	+
Hydrocarbons	
Gasoline	+
Diesel	+
Kerosene	+
Lyes	
Ammonia water 25 %	+
Sodium carbonate 25 %	+
sodium hydroxide solution 40 %	+
Esters	
Butyl acetate	+
Ethyl acetate	+
Ketones	
Acetone	+
Other solvents	
Glycol ether	+
Alcohols	
Butyl alcohol	+
Ethyl alcohol	+
Glycol	+
Glycerine	+
Isopropyl alcohol	+
Methyl alcohol	+

Table 2: Chemical resistance of Basotect® G+

**Product safety
and environmental**

Basotect® is produced without the use of halogenated hydrocarbons. The product is not hazardous to water. Basotect is delivered free of blowing agents and is not subject to labelling requirements under the German Hazardous Material Regulations.

Waste from Basotect can be recycled for purposes of heat and material recovery. Flake composite foams made of the same material and having densities ranging from 25 to 100 kg/m³ exhibit outstanding sound absorption in the lower and medium frequency ranges. Loose flake filling has already been successfully installed in hollow spaces of suspended ceilings with the objective of improving their acoustic properties. Flakes made of Basotect have also already been used as a binder for liquids.

Human ecology

Basotect G+ fulfils the current valid human ecology requirements of the Öko-Tex® Standard 100 in Product Class II for textiles with direct skin contact due to its particularly low emissions.

The Öko-Tex® Standard 100 is a global standard testing and certification system for raw, intermediate and final textile goods throughout all processing stages with the goal of comprehensively ensuring zero hazardous emissions. The hazardous substance testing comprises banned and legally regulated substances, chemicals which are harmful to health and parameters of health protection.

**Additional technical
information**

Detailed technical information can be obtained from:

BASF SE
GBU Specialty Plastics
www.basotect.de
(basotect@basf.com)

Safety

The information and instructions provided in the **Safety Data Sheet** have to be adhered to when this product is handled. For the rest, all preventive and occupational-safety **protection measures** that apply to the handling of chemicals **must be observed**.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



Get Your Obligation Free Quote

Contact Us

📍 Unit 5 16-18 Riverland Drive
Loganholme 4129
(By Appointment Only)

☎ 07 3287 7647

✉ info@soundproofwarehouse.com.au

🕒 Open 7 Days 9am - 5pm